

## Product Data Sheet

# PROTAN QUALITY 710 Symetricon laquered

### Product description

PVDF (water-based) laquered surface.

### Suitable applications

Soft skin buildings.

### Technical characteristics:

Properties	Test method	Typical values
Base fabric		Polyester, 1670dtex, Tricot
Coating		PVC
Yarn construction warp-weft		7,1x7,1
Width, cm	EN 1848-2	204
Weight, g/m <sup>2</sup>	EN 1849-2	1000
Tear resistance (L/T), N	EN 12310-2	850/750
Tensile strength (L/T), N/5cm	EN 12311-2	3900/3500
Elongation (L/T), %	EN 12311-2	21/22
Adhesion, N/5cm	DIN 53357	≥80
Temperature resistance, °C	EN 495-5	-30
Flame retardant	EN ISO 11925-2	Satisfactory

Typical values are average values from the production.

### Standard colours:

Colours on request