

## Product Data Sheet

# PROTAN QUALITY 404

### Suitable applications

Inner cover soft skin buildings. Scaffolding.

### Technical characteristics:

Properties	Test method	Typical values
Base fabric		Polyester, 1100dtex, Tricot
Coating		PVC
Yarn construction warp-weft		4,3x4,3
Width, cm	EN 1848-2	204
Weight, g/m2	EN 1849-2	550
Tear resistance (L/T), N	EN 12310-2	250/250
Tensile strength (L/T), N/5cm	EN 12311-2	1600/1400
Elongation (L/T), %	EN 12311-2	≥15
Adhesion, N/5cm	DIN 53357	≥65
Temperature resistance, °C	EN 495-5	-30
Fire classification according to NS-EN 13501-1:2007+A1:2009	EN ISO 11925/ EN13823	Reaction to fire class: B-s2,d0

Typical values are average values from the production.

### Standard colour:

Protan colour code: 001 (white)

### Approvals:

- Documentation SINTEF Certification PS 1706
- Swedish Technical approval 2935/81
- Danish Approval MK 6.10/0573

