

Product Data Sheet

PROTAN QUALITY 430

Suitable applications

Flat tarpaulins.

Technical characteristics:

Properties	Test method	Typical values
Base fabric		Polyester, 1100dtex, plain weave
Coating		PVC
Yarn construction warp-weft		7x7
Width, cm	EN 1848-2	204
Weight, g/m2	EN 1849-2	550
Tear resistance (L/T), N	DIN 53356	400/250
Tensile strength (L/T), N/5cm	EN 12311-2	2100/1900
Elongation (L/T), %	EN 12311-2	≥15
Adhesion, N/5cm	DIN 53357	≥80
Temperature resistance, °C	EN 495-5	-30
Flame retardant	DIN 75200	Satisfactory

Typical values are average values from the production.

Standard colours:

Protan colour codes: 001 (white), 118 (red), 664 (blue) and 991 (grey)
Other colours on request

Approvals:

-Documentation No.SINTEF EA-171